

Corrispondenze
Comparable standards

SIAU	DIN	W.N.	AFNOR	BS	AISI/SAE
-	-	-	-	-	-

Composizione - Chemical analysis

C	Mn	Si	Cr	Ni	Mo	Cu	Nb	V
≤ .35	.60±1.05	.10±.35	≤ .30	≤ .40	≤ .12	≤ .40	≤ .02	≤ .05
Σ (Cr+Mo) ≤.32			Σ (Cr+Ni+Mo+Cu+V) ≤1.00					
CE [C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15] ≤0,47								

**Caratteristiche
meccaniche**
Mechanical properties

Stato Condition	Re min. N/mm ²	Rm N/mm ²	A 4d min. %	Z min. %	KV-46° min J
Normalizzato Normalized	250	485÷655	22	30	20